

ZCB								
lab./stan.	sednutí (mm)		rozlití (mm)			objem.h.(kg/m ³)		vzduch%
	1	oprav.	1	2	prum.	1	oprav.	
1	200	200						5,2
2								
3	150	150	450	430	440	2339	2340	5,1
4								
5	130	130				2353	2350	4,8
6	160	160	480	490	485	2300	2300	5,4
7	170	170				2310	2310	4,8
8	170	170	390	385	390	2337	2340	4,2
9	160	160	390		390	2370	2370	4,3
10	195	195	440		440	2340	2340	4,2
p		8			5		7	8
m		167			429		2336	4,8
sm.o.		22,8			40,1		23,7	0,47
max.		192			467		2350	5,7
min.		142			392		2321	3,8

ZZB								
lab./stan.	objem.hmot. (kg/m ³)				pevnost(MPa)			
	1	2	3	prum.	1	2	3	prum.
1	2290	2310	2300	2300	36,5	41,0	36,0	37,8
2	2390	2400	2390	2393	57,0	56,5	59,5	57,7
3	2330	2310	2320	2320	47,5	48,5	49,0	48,3
4	2320	2330	2330	2327	43,5	45,5	47,0	45,3
5	2340	2350	2340	2343	47,0	48,0	45,5	46,8
6	2340	2370	2360	2357	45,5	46,0	47,0	46,2
7	2290	2310	2310	2303	46,0	46,5	46,5	46,3
8	2370	2370	2380	2373	49,5	47,5	44,5	47,2
9	2340	2340	2340	2340	45,4	48,0	46,5	46,6
10	2390	2380	2370	2380	51,0	50,5	48,0	49,8
p				10				10
m				2344				47
sm.o.				32,0				4,8
max.				2373				50
min.				2315				44

ZBK- čtení na tvrdoměru												
lab./stan.	1	2	3	4	5	6	7	8	9	sm.o.	prům.	typ
2	44	45	47	44	44	45	44	45	47	1,22	45,0	N - 13
3	43	46	48	47	48	46	46	48	47	1,59	46,6	NR-10
6	46	43	46	46	46	40	46	43	35	2,27	44,5	NR-10
7	46	44	46	44	40	44	45	48	46	2,22	44,8	N 34
8	44	46	45	46	46	46	48	48	48	1,41	46,3	N 26
9	45	44	43	48	47	44	45	44	45	1,58	45,0	LR 3
10	50	46	48	48	50	47	46	48	44	1,94	47,4	N
p											7	
m											45,4	
sm.o.											1,5	
max.											48,4	
min.											42,4	