

MPZ 1997 - Asfalty a asfaltová pojiva

lab.	PENETRACE				BOD MĚKNUTÍ			
	A 90/45P			poznámka	A 90/45P			poznámka
	1	2	průměr		1	2	průměr	
1	84,7	86,0	85,4		44,3	44,8	44,6	
2	62,7	63,3	63,0		44,0	45,0	44,5	
3	80,0	80,0	80,0		43,1	43,2	43,2	
4	79,0	82,0	80,5		45,0	45,2	45,0	
5	85,3	87,7	86,5		45,0	46,0	45,5	
6	79,0	79,0	79,0		46,8	46,7	46,8	
7	93,0	-	93,0		44,5	44,5	44,5	
8	83,0	84,0	83,5		44,0	44,3	44,1	
9	75,0	76,0	75,5		47,2	47,0	47,1	
10	96,2	93,0	94,6		47,0	47,3	47,2	
11	95,0	93,0	94,0		46,2	46,4	46,3	
12	82,0	84,0	83,0		46,6	47,2	46,9	
13	72,3	73,0	72,7		45,8	46,3	46,1	
14	80,0	84,0	82,0		43,6	43,5	43,6	
15	80,0	80,0	80,0		43,5	42,6	43,1	
16	81,0	81,0	81,0		43,2	43,4	43,3	
17	84,1	83,9	84,0		44,3	44,2	44,3	
18	83,9	83,8	83,9		44,6	44,4	44,5	
19	85,4	86,3	85,9		44,2	44,1	44,2	
20	71,0	70,0	71,5		45,8	45,6	45,7	
21	81,4	81,0	81,2		42,2	42,4	42,3	
22	88,7	88,3	88,5		44,8	44,6	44,7	
23	83,0	81,0	82,0		42,0	42,2	42,1	
24	76,7	75,7	76,2		45,7	45,7	45,7	
25	97,0	97,0	97,0		45,1	45,1	45,1	
26	88,0	88,0	88,0		46,3	46,3	46,3	
27	79,0	80,0	79,5		44,4	44,6	44,5	
28	85,7	88,0	86,9		45,1	44,5	44,9	
29	78,0	78,0	78,0		45,4	45,5	45,5	
30	79,0	-	79,0		44,6	44,8	44,7	
31	85,5	-	85,5		44,0	44,5	44,3	
32	89,8	86,9	88,4		47,1	47,2	47,2	
33	57,2	56,8	57,0		48,9	48,5	48,7	
34	89,0	90,0	89,5		45,0	45,0	45,0	
35	98,0	98,0	98,0		41,0	41,0	41,0	
36	88,0	87,5	87,8		46,2	45,5	45,9	
37	93,0	93,0	93,0		46,1	46,1	46,1	
38					46,3	46,4	46,4	
39	71,0	71,0	71,0		45,2	45,3	45,3	
40	85,6	86,3	86,0		44,7	44,5	44,6	
41	87,0	85,0	86,0		43,2	43,9	43,6	
42	90,0	91,0	91,0		44,9	44,7	44,8	
43	75,0	74,0	74,5		49,5	49,0	49,3	
p			39				43	
m			78,84				45,08	
sm.o.			8,158				1,636	