

MPZ 1998 - Asfalty a asfaltová pojiva

lab.	PENETRACE				BOD MĚKNUTÍ			
	A 80			poznámka	A 80			poznámka
	1	2	průměr		1	2	průměr	
1	98,4	97,4	97,9		47,0	46,9	46,95	
2	80,0	80,0	80,0		44,1	44,1	44,1	
3	79,0	79,0	79,0		45,1	44,7	44,9	
4	60,0	60,0	60,0		44,8	44,8	44,8	
5	80,0	80,0	80,0		46,3	46,5	46,4	
6	81,0	81,0	81,0		49,4	50,2	49,8	
7	71,0	74,0	72,5		48,0	48,4	48,2	
8	74,0	75,0	74,5		46,8	47,0	46,9	
9	88,0	88,0	88,0		44,7	44,8	44,8	
10	69,5	68,8	69,2		42,0	43,0	42,5	
11	75,7	78,3	77,0		46,8	47,4	47,1	
12	63,0	64,0	63,5		49,2	48,8	49,0	
13	78,0	79,0	78,5		46,0	46,9	46,5	
14	78,0	77,0	77,5		46,1	45,8	46,0	
15	87,0	88,0	87,5		46,8	47,0	46,9	
16	84,0	83,0	83,5		46,6	46,6	46,6	
17	79,0	78,0	78,5		44,1	44,3	44,2	
18					45,1	45,0	45,1	
19	90,0	91,0	90,5		46,0	46,0	46,0	
20	83,0	84,0	83,5		47,5	47,5	47,5	
21	73,6	74,0	73,8		47,0	47,4	47,2	
22	79,0	82,0	80,5		46,5	47,0	46,8	
23	86,1	90,6	88,4		45,5	46,0	45,8	
24	72,5	72,2	72,4		45,3	45,6	45,5	
25	73,2	73,8	73,5		45,9	45,7	45,8	
26	80,3	80,7	80,5		44,2	44,5	44,4	
27	83,3	80,7	82,0		47,5	47,3	47,4	
28	87,0	86,0	86,5		44,2	44,8	44,5	
29	81,7	82,7	82,2		47,5	47,0	47,3	
30					42,4	42,6	42,5	
31	82,0	82,0	82,0		44,5	45,0	44,8	
32	82,3	83,0	82,7		47,0	47,5	47,3	
33	78,0	78,0	78,0					
34	71,0	71,0	71,0		47,8	48,0	47,9	
35	79,0	79,0	79,0					
36	50,3	49,0	49,7		49,9	50,8	50,4	
37	84,7	83,7	84,2		45,8	46,0	45,9	
38	75,0	75,0	75,0		45,4	45,8	45,6	
39	78,0	77,0	77,5		47,0	47,5	47,3	
40	55,0	54,0	54,5		46,0	46,2	46,1	
41	81,5	82,8	82,2		47,2	46,9	47,1	
42					44,7	44,9	44,8	
43	87,0	86,7	86,9		46,2	46,4	46,3	
p			39				41	
m			78,84				46,2	
sm.o.			8,158				1,664	