

MPZ 1999 - Asfalty a asfaltová pojiva

lab.	PENETRACE				BOD MĚKNUTÍ			
	A 80			poznámka	A 80			poznámka
	1	2	průměr		1	2	průměr	
1	77,0	76,0	76,5		48,2	48,2	48,2	
2	72,0	73,0	72,5		47,0	46,9	47,0	
3	68,0	69,0	68,5		46,4	46,2	46,3	
4	75,0	75,0	75,0		47,2	47,2	47,2	
5	79,0	76,0	77,5		47,8	48,0	47,9	
6	79,0	80,0	79,5		47,8	48,2	48,0	
7	75,3	75,0	75,2		46,2	45,5	45,9	
8	87,0	89,0	88,0		47,8	48,2	48,0	
9	72,0	72,0	72,0		47,7	47,6	47,7	
10	98,1	97,2	97,7		48,6	48,7	48,7	
11	75,3	75,0	75,2		47,8	48,2	48,0	
12	71,4	70,7	71,1		47,1	47,3	47,2	
13	78,0	78,0	78,0		47,6	47,8	47,7	
14	77,0	77,0	77,0		50,0	50,2	50,1	
15	77,0	78,0	77,5		50,0	50,2	50,1	
16	82,0	80,0	81,0		47,2	47,4	47,3	
17	78,3	78,7	78,5		47,4	47,6	47,5	
18	73,6	73,7	73,7		45,8	46,4	46,1	
19	81,0	82,0	81,5		48,6	49	48,8	
20	67,0	65,0	66,0		46,5	46,5	46,5	
21	78,0	77,0	77,5		46,6	46,7	46,7	
22	76,0	76,0	76,0		47,0	47,0	47,0	
23	77,0	76,0	76,5		47,3	47,9	47,6	
24	75,6	74,8	75,2		48,0	48,2	48,1	
25	78,3	77,3	77,8		47,8	47,5	47,7	
26	73,7	72,7	73,2		49,0	48,0	48,5	
27	76,3	77,5	76,9		46,8	47,1	47,0	
28	77,1	76,8	77,0		47,1	47,5	47,3	
29	72,0	71,0	71,5					
30	73,0	77,3	75,2		45,6	45,8	45,7	
31	70,7	70,7	70,7		49,2	49,4	49,3	
32	ne				47,5	47,5	47,5	
33	80,0	79,0	79,5		48,0	48,0	48,0	
34	76,8	77	76,9		47,8	48,2	48,0	
35	85,0	83,0	84,0		ne			
36	73,0	73,0	73,0		49,8	49,8	49,8	
37	71,4	71,3	71,4		ne			
38	77,0	76,0	76,5		47,8	48	47,9	
39	84,3	84,6	84,5		48,5	48,5	48,5	
40	76,0	77,0	76,5		48,0	47,9	48,0	
41	77,1	76,9	77,0		47,2	47,4	47,3	
42	76,7	76,2	76,5		46,0	46,1	46,1	
43	68,5	68,7	68,6		49,2	50,2	49,7	
44	71,0	72,0	71,5		49,0	48,6	48,8	
45	79,0	80,0	79,5		48,7	49,0	48,9	
46	71,0	72,0	71,5		46,8	47,0	46,9	
47	78,0	81,0	79,5		46,2	46,5	46,4	
48	75,0	73,0	74,0		49,0	49,3	49,2	
49	80,0	81,0	80,5		48,0	48,4	48,2	
50	77,3	78,3	77,8		48,2	47,7	48,0	
51	64,0	64,0	64,0		48,7	46,2	47,5	
52	79,0	80,7	79,9		47,7	48,1	47,9	
53	73,7	72,3	73,0		49,7	49,3	49,5	
p			51				50	
m			75,8				47,8	
sm.o.			4,480				1,077	